

## Technical data sheet

### AET Lézaud GmbH

Am Hottenwald 8  
66606 St. Wendel

Tel.: 0049 (0) 6851 / 97394 - 0  
Fax: 0049 (0) 6851 / 97394 - 44  
Mail: industrie@lezaud.de  
Web: www.lezaud.de

## Sheets LEZ-SAN 65

Pos.	Parameter	Value
	Elastomer base	TPE (PP/EPDM)
	Geometry	Sheet
	Density	0,97 g/cm <sup>3</sup>
	Density standard	DIN 53479
	Hardness	65 +/-5 Shore A
	Hardness standard	DIN 53505
	Temperature resistance	-45°C to +135°C
	Colour	light beige
	Compression set	23% at 25°C, 168 h, 36% at 100°C, 168 h
	Compression set standard	ASTM D995 B
	Module 100	2,3 MPa
	Module 100 standard	DIN 53504
	Elongation at break	> 450 %
	Elongation at break standard	DIN 53504
	Tensile strength	> 6,5 MPa
	Tensile strength standard	DIN 53504

### Pos. Conformities

FDA 21 CFR §177.2600; NSF51; UL gelistet (Nr. QMFZ2.E80017); 2003/11/EG; EU 10/2011 (globale Migration); EG 1935/2004 (globale Migration)

Pos\* A= Outside; IN= Inside, S1= Page1; S2= Page2

The values of this specification originate from the ongoing tests of the mixture of miel's standard test specimens and represent mean values. They correspond to the current state of knowledge and experience. They are not intended to guarantee the properties of end products. The information in this data sheet is a description of typical properties. They are only intended to provide the user with an orientation aid and some suggestions for his application. It is the user's responsibility to check the suitability of our product for his own purposes in a specific application.

We strive to continuously improve our products and reserve the right to modify and adapt the data sheet and our mixtures with regard to the material properties. These will be documented with a new modification status (date).