

Technical data sheet

AET Lézaud GmbH

Am Hottenwald 8
66606 St. Wendel

Tel.: 0049 (0) 6851 / 97394 - 0
Fax: 0049 (0) 6851 / 97394 - 44
Mail: industrie@lezaud.de
Web: www.lezaud.de

Sheets LEZ-SILEXP 20R

Pos.	Parameter	Value
	Elastomer base	Silicone foam
	Geometry	Sheet
	Density	250 +/-40 kg/m ³
	Density standard	ISO 845
	Hardness	20 +/-5 Shore A
	Hardness standard	ASTM D2240
	Temperature resistance	-70°C to +200°C
	Colour	white
	Compression set	max. 15 % at 70°C, 22 h
	Compression set standard	ISO 1856
	Elongation at break	min. 150 %
	Elongation at break standard	ISO 1798
	Tear resistance	1,2 N/mm ²
	Tear resistance standard	ISO 1798
	Thermal conductivity	6,4 W.m E-1 .K E-1
	Thermal conductivity standard	VDE 0304

Pos. Conformities

Pos* A= Outside; IN= Inside, S1= Page1; S2= Page2

The values of this specification originate from the ongoing tests of the mixture of miel's standard test specimens and represent mean values. They correspond to the current state of knowledge and experience. They are not intended to guarantee the properties of end products. The information in this data sheet is a description of typical properties. They are only intended to provide the user with an orientation aid and some suggestions for his application. It is the user's responsibility to check the suitability of our product for his own purposes in a specific application.

We strive to continuously improve our products and reserve the right to modify and adapt the data sheet and our mixtures with regard to the material properties. These will be documented with a new modification status (date).