

Technical data sheet

Sheets LEZ-SILFLON

AET Lézaud GmbH

Am Hottenwald 8
66606 St.Wendel

Tel.: 0049 (0) 6851 / 97394 - 0
Fax: 0049 (0) 6851 / 97394 - 44
Mail: industrie@lezaud.de
Web: www.lezaud.de

Pos.	Parameter	Value
	Elastomer base	Silicone/PTFE
	Geometry	Sheet
	Density	Silicone: 1,1 +/-0,05 g/cm ³ , PTFE: 2,16 g/cm ³
	Density standard	DIN 53479
	Hardness	Silicone: 45 +/-5 Shore A, PTFE 65 +/-5 Shore D
	Hardness standard	DIN 53505
	Temperature resistance	-60°C to +220°C
	Colour	Silicone: white, PTFE: red
	Elongation at break	Silikon: >450%
	Elongation at break standard	DIN 53504
	Elongation at break	PTFE: 380%
	Elongation at break standard	DIN 53504
	Tear resistance	PTFE: 29 N/mm ²
	Tear resistance standard	DIN 53504
	Tensile strength	Silikon: >6,0 N/mm ²
	Tensile strength standard	DIN 53504

Pos. Conformities

Pos* A= Outside; IN= Inside, S1= Page1,;S2= Page2

The values of this specification originate from the ongoing tests of the mixture of miel's standard test specimens and represent mean values. They correspond to the current state of knowledge and experience. They are not intended to guarantee the properties of end products. The information in this data sheet is a description of typical properties. They are only intended to provide the user with an orientation aid and some suggestions for his application. It is the user's responsibility to check the suitability of our product for his own purposes in a specific application.

We strive to continuously improve our products and reserve the right to modify and adapt the data sheet and our mixtures with regard to the material properties. These will be documented with a new modification status (date).