

Technical data sheet

AET Lézaud GmbH

Am Hottenwald 8
66606 St. Wendel

Tel.: 0049 (0) 6851 / 97394 - 0
Fax: 0049 (0) 6851 / 97394 - 44
Mail: industrie@lezaud.de
Web: www.lezaud.de

Cords LEZ-EPEM 60

Pos.	Parameter	Value
	Elastomer base	EPDM
	Geometry	Cord
	Density	1,18 +/-0,02 g/cm ³
	Density standard	DIN ISO 7619-1
	Hardness	60 +/-5 Shore A
	Hardness standard	DIN EN 1183-11
	Temperature resistance	-35°C to +120°C
	Colour	black
	Elongation at break	250 %
	Elongation at break standard	DIN 53504
	Compression set	20 % at 100°C, 22 h
	Compression set standard	DIN ISO 815
	Tear propagation resistance	25 kN/m
	Tear propagation resistance standard	DIN ISO 34-1 C
	Tensile strength	10 MPa
	Tensile strength standard	DIN 53504

Pos. Conformities

Pos* A= Outside; IN= Inside, S1= Page1; S2= Page2

The values of this specification originate from the ongoing tests of the mixture of miel's standard test specimens and represent mean values. They correspond to the current state of knowledge and experience. They are not intended to guarantee the properties of end products. The information in this data sheet is a description of typical properties. They are only intended to provide the user with an orientation aid and some suggestions for his application. It is the user's responsibility to check the suitability of our product for his own purposes in a specific application.

We strive to continuously improve our products and reserve the right to modify and adapt the data sheet and our mixtures with regard to the material properties. These will be documented with a new modification status (date).