

## Technical data sheet

### AET Lézaud GmbH

Am Hottenwald 8  
66606 St.Wendel

Tel.: 0049 (0) 6851 / 97394 - 0  
Fax: 0049 (0) 6851 / 97394 - 44  
Mail: industrie@lezaud.de  
Web: www.lezaud.de

## Cords LEZ-NIT

Pos.	Parameter	Value
	Elastomer base	NBR
	Geometry	Cord
	Density	1,3 +/-0,1 g/cm <sup>3</sup>
	Density standard	PN ISO 2781+AC1
	Hardness	70 +/-5 Shore A
	Hardness standard	PN 80/C-04238
	Temperature resistance	-40°C to +80°C
	Colour	black
	Elongation at break	200 %
	Elongation at break standard	PN ISO 37
	Tear resistance	7 MPa
	Tear resistance standard	PN ISO 37

### Pos. Conformities

Pos\* A= Outside; IN= Inside, S1= Page1; S2= Page2

The values of this specification originate from the ongoing tests of the mixture of miel's standard test specimens and represent mean values. They correspond to the current state of knowledge and experience. They are not intended to guarantee the properties of end products. The information in this data sheet is a description of typical properties. They are only intended to provide the user with an orientation aid and some suggestions for his application. It is the user's responsibility to check the suitability of our product for his own purposes in a specific application.

We strive to continuously improve our products and reserve the right to modify and adapt the data sheet and our mixtures with regard to the material properties. These will be documented with a new modification status (date).