

Technical data sheet

AET Lézaud GmbH

Am Hottenwald 8
66606 St.Wendel

Tel.: 0049 (0) 6851 / 97394 - 0
Fax: 0049 (0) 6851 / 97394 - 44
Mail: industrie@lezaud.de
Web: www.lezaud.de

Cords LEZ-SAN 65

| Pos. | Parameter | Value |
|------|------------------------------|---|
| | Elastomer base | TPE (PP/EPDM) |
| | Geometry | Cord |
| | Density | 0,97 g/cm ³ |
| | Density standard | DIN 53479 |
| | Hardness | 65 +/-5 Shore A |
| | Hardness standard | DIN 53505 |
| | Temperature resistance | -45°C to +135°C |
| | Colour | light beige |
| | Compression set | 23% at 25°C, 168 h, 36% at 100°C, 168 h |
| | Compression set standard | ASTM D995 B |
| | Module 100 | 2,3 MPa |
| | Module 100 standard | DIN 53504 |
| | Elongation at break | >450% |
| | Elongation at break standard | DIN 53504 |
| | Tensile strength | >6,5 MPa |
| | Tensile strength standard | DIN 53504 |

Pos. Conformities

FDA 21 CFR §177.2600;NSF51;UL gelistet (Nr. QMFZ2.E80017);2003/11/EG;EU 10/2011 (globale Migration);EG 1935/2004 (globale Migration)

Pos* A= Outside; IN= Inside, S1= Page1;S2= Page2

The values of this specification originate from the ongoing tests of the mixture of miel's standard test specimens and represent mean values. They correspond to the current state of knowledge and experience. They are not intended to guarantee the properties of end products. The information in this data sheet is a description of typical properties. They are only intended to provide the user with an orientation aid and some suggestions for his application. It is the user's responsibility to check the suitability of our product for his own purposes in a specific application.

We strive to continuously improve our products and reserve the right to modify and adapt the data sheet and our mixtures with regard to the material properties. These will be documented with a new modification status (date).