

Technical data sheet

AET Lézaud GmbH

Am Hottenwald 8
66606 St.Wendel

Tel.: 0049 (0) 6851 / 97394 - 0
Fax: 0049 (0) 6851 / 97394 - 44
Mail: industrie@lezaud.de
Web: www.lezaud.de

Tube LEZ-NEO

| Pos. | Parameter | Value |
|------|------------------------------|--------------------------------|
| | Elastomer base | CR |
| | Geometry | Tube |
| | Density | 1,29 +/-0,02 g/cm ³ |
| | Density standard | DIN 53479 |
| | Hardness | 65 +/-5 Shore A |
| | Hardness standard | DIN 53505 |
| | Temperature resistance | -30°C to +90°C |
| | Colour | black |
| | Elongation at break | 200 % |
| | Elongation at break standard | DIN 53504 |
| | Compression set | 30% at 70°C, 22 h |
| | Compression set standard | DIN 53517 |
| | Tear resistance | 20 kN/m |
| | Tear resistance standard | ISO 34 C |
| | Tensile strength | 10,5 MPa |
| | Tensile strength standard | DIN 53504 |

Pos. Conformities

Pos* A= Outside; IN= Inside, S1= Page1; S2= Page2

The values of this specification originate from the ongoing tests of the mixture of miel's standard test specimens and represent mean values. They correspond to the current state of knowledge and experience. They are not intended to guarantee the properties of end products. The information in this data sheet is a description of typical properties. They are only intended to provide the user with an orientation aid and some suggestions for his application. It is the user's responsibility to check the suitability of our product for his own purposes in a specific application.

We strive to continuously improve our products and reserve the right to modify and adapt the data sheet and our mixtures with regard to the material properties. These will be documented with a new modification status (date).