

Technical data sheet

AET Lézaud GmbH

Am Hottenwald 8
66606 St. Wendel

Tel.: 0049 (0) 6851 / 97394 - 0
Fax: 0049 (0) 6851 / 97394 - 44
Mail: industrie@lezaud.de
Web: www.lezaud.de

Tube LEZ-PAM

Pos.	Parameter	Value
	Elastomer base	PA
	Geometry	Tube
	Density	1,02 g/cm ³
	Density standard	ISO 1183
	Hardness	63 Shore D
	Hardness standard	ISO 868
	Temperature resistance	-40°C to +90°C
	Colour	nature
	Bending modulus of elasticity	360 MPa
	Bending modulus of elasticity standard	ISO 527-1,2
	Throughput resistance	1E12 Ohm
	Throughput resistance standard	IEC 60093
	Dielectric strength	32 kV/mm
	Dielectric strength standard	IEC 60243-1
	Tensile strength	25 MPa
	Tensile strength standard	ISO 527-1,2

Pos. Conformities

Pos* A= Outside; IN= Inside, S1= Page1; S2= Page2

The values of this specification originate from the ongoing tests of the mixture of miel's standard test specimens and represent mean values. They correspond to the current state of knowledge and experience. They are not intended to guarantee the properties of end products. The information in this data sheet is a description of typical properties. They are only intended to provide the user with an orientation aid and some suggestions for his application. It is the user's responsibility to check the suitability of our product for his own purposes in a specific application.

We strive to continuously improve our products and reserve the right to modify and adapt the data sheet and our mixtures with regard to the material properties. These will be documented with a new modification status (date).