

Technical data sheet

AET Lézaud GmbH

Am Hottenwald 8
66606 St.Wendel

Tel.: 0049 (0) 6851 / 97394 - 0
Fax: 0049 (0) 6851 / 97394 - 44
Mail: industrie@lezaud.de
Web: www.lezaud.de

Tube LEZ-SITEC-RTPR

Pos.	Parameter	Value
	Elastomer base	Silicone with monofilament insert
	Geometry	Tube
	Density	1,16 +/- 0,05 g/cm ³
	Density standard	DIN 53479 A
	Hardness	70 +/-5 Shore A
	Hardness standard	DIN 53505
	Temperature resistance	-60°C to +180°C
	Colour	inside: transparent, outside: red coated
	Compression set	35 % at 175°C, 22 h
	Compression set standard	DIN 53517
	Elongation at break	500 %
	Elongation at break standard	DIN 53504 S1
	Tear resistance	11,3 %
	Tear resistance standard	DIN 53504 S1
	Rebound resilience	53 %
	Rebound resilience standard	DIN 53512
	Tear propagation resistance	25 N/mm
	Tear propagation resistance standard	ASTM D624 B

The burst pressure is a statistical, non-binding value that was determined at 20°C and with water as the pressure carrier medium. Higher temperatures and the use of other types of media can reduce the pressure resistance.

Pos. Conformities

Pos* A= Outside; IN= Inside, S1= Page1, S2= Page2

The values of this specification originate from the ongoing tests of the mixture of miel's standard test specimens and represent mean values. They correspond to the current state of knowledge and experience. They are not intended to guarantee the properties of end products. The information in this data sheet is a description of typical properties. They are only intended to provide the user with an orientation aid and some suggestions for his application. It is the user's responsibility to check the suitability of our product for his own purposes in a specific application.

We strive to continuously improve our products and reserve the right to modify and adapt the data sheet and our mixtures with regard to the material properties. These will be documented with a new modification status (date).