

Technical data sheet

AET Lézaud GmbH

Am Hottenwald 8
66606 St. Wendel

Tel.: 0049 (0) 6851 / 97394 - 0
Fax: 0049 (0) 6851 / 97394 - 44
Mail: industrie@lezaud.de
Web: www.lezaud.de

Tube LEZ-VAC

Pos.	Parameter	Value
	Elastomer base	NR
	Geometry	Tube
	Density	1,2 +/- 0,4 g/cm ³
	Density standard	DIN 53479
	Hardness	50 +/-5 Shore A
	Hardness standard	DIN 53505
	Temperature resistance	-40°C to +70°C
	Colour	red
	Elongation at break	min. 500 %
	Elongation at break standard	DIN 53504
	Compression set	14 % at 70°C, 22 h
	Compression set standard	DIN 53517
	Tear resistance	min. 7 MPa
	Tear resistance standard	DIN 53504
	Tear resistance outside	5 N/mm
	Tear resistance outside standard	DIN 53515

Pos. Conformities

Pos* A= Outside; IN= Inside, S1= Page1; S2= Page2

The values of this specification originate from the ongoing tests of the mixture of miel's standard test specimens and represent mean values. They correspond to the current state of knowledge and experience. They are not intended to guarantee the properties of end products. The information in this data sheet is a description of typical properties. They are only intended to provide the user with an orientation aid and some suggestions for his application. It is the user's responsibility to check the suitability of our product for his own purposes in a specific application.

We strive to continuously improve our products and reserve the right to modify and adapt the data sheet and our mixtures with regard to the material properties. These will be documented with a new modification status (date).