

Technical data sheet

AET Lézaud GmbH

Am Hottenwald 8
66606 St. Wendel

Tel.: 0049 (0) 6851 / 97394 - 0
Fax: 0049 (0) 6851 / 97394 - 44
Mail: industrie@lezaud.de
Web: www.lezaud.de

Tube LEZ-VITMET 70/ES

Pos.	Parameter	Value
	Elastomer base	FKM with stainless steel braiding
	Geometry	Tube
	Density	1,85 +/- 0,1 g/cm ³
	Density standard	DIN 53479
	Hardness	70 +/-5 Shore A
	Hardness standard	DIN 53505
	Temperature resistance	-15°C to +200°C
	Colour	inside: black, outside: silver
	Module 100	5,7 MPa
	Module 100 standard	DIN 53504
	Elongation at break	>200 %
	Elongation at break standard	DIN 53504
	Tensile strength	>8,5 MPa
	Tensile strength standard	DIN 53504

Pos. Conformities

Pos* A= Outside; IN= Inside, S1= Page1; S2= Page2

The values of this specification originate from the ongoing tests of the mixture of miel's standard test specimens and represent mean values. They correspond to the current state of knowledge and experience. They are not intended to guarantee the properties of end products. The information in this data sheet is a description of typical properties. They are only intended to provide the user with an orientation aid and some suggestions for his application. It is the user's responsibility to check the suitability of our product for his own purposes in a specific application.

We strive to continuously improve our products and reserve the right to modify and adapt the data sheet and our mixtures with regard to the material properties. These will be documented with a new modification status (date).