

## Technical data sheet

### Plugs LEZ-GOM grey line D

#### AET Lézaud GmbH

Am Hottenwald 8  
66606 St. Wendel

Tel.: 0049 (0) 6851 / 97394 - 0  
Fax: 0049 (0) 6851 / 97394 - 44  
Mail: industrie@lezaud.de  
Web: www.lezaud.de

Pos.	Parameter	Value
	Elastomer base	NR/SBR
	Geometry	Plugs
	Density	1,18 +/-0,02 g/cm <sup>3</sup>
	Density standard	DIN 52479
	Hardness	40 +/-5 Shore A
	Hardness standard	DIN 53505
	Temperature resistance	-30°C to +60°C
	Colour	grey
	Elongation at break	>690%
	Elongation at break standard	DIN 53505
	impact elasticity	>60%
	impact elasticity standard	DIN 53512
	Tensile strength	>10 N/mm <sup>2</sup>
	Tensile strength standard	DIN 53504

#### Pos. Conformities

Pos\* A= Outside; IN= Inside, S1= Page1; S2= Page2

The values of this specification originate from the ongoing tests of the mixture of miel's standard test specimens and represent mean values. They correspond to the current state of knowledge and experience. They are not intended to guarantee the properties of end products. The information in this data sheet is a description of typical properties. They are only intended to provide the user with an orientation aid and some suggestions for his application. It is the user's responsibility to check the suitability of our product for his own purposes in a specific application.

We strive to continuously improve our products and reserve the right to modify and adapt the data sheet and our mixtures with regard to the material properties. These will be documented with a new modification status (date).