

Technical data sheet

Plugs LEZ-VIT black line S

AET Lézaud GmbH

Am Hottenwald 8
66606 St. Wendel

Tel.: 0049 (0) 6851 / 97394 - 0
Fax: 0049 (0) 6851 / 97394 - 44
Mail: industrie@lezaud.de
Web: www.lezaud.de

Pos.	Parameter	Value
	Elastomer base	FKM
	Geometry	Plugs
	Density	1,81 +/- 0,03 g/cm ³
	Density standard	DIN ISO 1183
	Hardness	70 +/- 5 Shore A
	Hardness standard	DIN ISO 7619
	Temperature resistance	-18°C to +200°C
	Colour	black
	Abrasion	205 mm ²
	Abrasion standard	DIN 53516
	Elongation at break	> 260 %
	Elongation at break standard	DIN 53504
	Compression set	8% at 175°C, 24 h
	Compression set standard	DIN ISO 815 B
	Rebound resilience	5 %
	Rebound resilience standard	DIN 53514
	Cross-linking	Bisphenol
	Tensile strength	> 6 N/mm ²
	Tensile strength standard	DIN 53504

Pos. Conformities

Pos* A= Outside; IN= Inside, S1= Page1; S2= Page2

The values of this specification originate from the ongoing tests of the mixture of miel's standard test specimens and represent mean values. They correspond to the current state of knowledge and experience. They are not intended to guarantee the properties of end products. The information in this data sheet is a description of typical properties. They are only intended to provide the user with an orientation aid and some suggestions for his application. It is the user's responsibility to check the suitability of our product for his own purposes in a specific application.

We strive to continuously improve our products and reserve the right to modify and adapt the data sheet and our mixtures with regard to the material properties. These will be documented with a new modification status (date).